Product Specification 😵



Article		Fenestrated Drape		
Specification No.		55 88 23		
Article No.		55 88 23, sterile goods 55 88 23/9 & 700 621, non-sterile goods		
1.	Description	Drape made of Mediwell super 2-ply turquoise, with fenestration and adhesive zone		
2.	Application	Patient drape		
3.	Production	The above mentioned drape is manufactured in hygienic conditions		
4.	Material composition	all of the materials used are <u>latex-free</u> !		
4.1	Basis drape MWS 2-ply			
•	Film	multiple ply PE film (PVC-free), turquoise		
•	Drylaid Nonwoven	80 % viscose <i>(without optical brighteners),</i> 20 % chem. binder, turquoise.		
•	Lamination	multiline glued compound		
4.2	Adhesive tape	skin friendly, synthetic caoutchouc adhesive on a polyester carrier		
4.3	Silicone paper	silicone glazed paper, white		
5.	Product properties	impermeable to fluids and bacteria in accordance with EN 13795, extremely		
drapeable.				
6. 6.1 •	Technical data <u>Dimensions</u> / Basis drape Length Width	60 cm ± 2 cm 50 cm ± 1 cm		
•	Fenestration	\varnothing 6 cm ± 1 cm		
6.1.1	Adhesive tape			
٠	Length	14 cm \pm 2 cm		

- Width
- Finger lift

12 cm ± 1 cm 1 cm, *lengthwise on both sides*

Quality Assurance:		
Date: 23.09.2022	Signature:	Lietzon

QSt 21 gültig ab 14.11.2016



STS MEDICAL GROUP SENGEVVALD

Article		Fenestrated Drape
Specification No.		55 88 23
	<i>Final folded dimensions</i> Length Width	20 cm ± 2 cm 9.5 cm ± 1 cm
6.2 • •	<u>Raw material</u> Film Basis weight Thickness	24 g/m² ± 10 % 50 μm ± 10 %
• • •	<i>Drylaid Nonwoven</i> Basis weight Absorption	28 g/m² ± 10 % > 240 ml/m²
•	<i>Silicone paper</i> Basis weight	90 g/m² ± 10 %

6.3 <u>Performance requirements</u>

- The material used to make this product exceeds the minimum requirements, in accordance with the pertinent parts of EN 13795.
- Individual values can be found in the corresponding material specification.



STS MEDICAL GROUP SENGEWALD

Article

Fenestrated Drape

Specification No.

55 88 23

- 7. Folding
- 7.1 Schematic diagram



all dimensions in cm

8. Packaging / *sterile goods*

- 8.1 Primary packaging
 - Paper
 - Film
- 8.2 Secondary packaging
 - Size
 - Dispenser contents
- 8.3 Transport packaging
 - Size
 - Contents
- 8.4 Sterilisation
- 8.5 Usability and storage

70 g/m² \pm 10 % PA/PE 85 μ m \pm 10 %, transparent

grade E / WTU 140 / W 110 / TB 140 310 x 125 x 284 mm ± 10 mm 55 pcs.

grade 1.40 B 800 x 294 x 316 mm ± 10 mm 330 (6 x 55) pcs.

- EtO sterilisation (in accordance with ISO 11135)
- 5 years, no direct exposure to sunshine



STS MEDICAL GROUP SENGEWALD

Article	Fenestrated Drape	
Specification No.	55 88 23	
 9. Packaging / non-sterile god 9.1 <i>Film bag</i> Size Film Contents 9.2 <i>Transport packaging</i> Size Contents Transport packaging lined w 	650 / 300 x 725 mm ± 10 mm PE film 40 μm ± 10 %, transparent 250 pcs. <i>grade 1.30 C</i> 645 x 295 x 235 mm ± 10 mm 250 pcs.	
9.3 Sterilisation9.3.1 Material properties after irrad	Sterilisation suitable for sterilisation by EtO gas and irradiation with 25 kGy. Material properties after irradiation After sterilisation by irradiation at rate of 50 kGy a linear decrease of values of 25 %	
9.4 Usability and storage packaging,	6 years from the delivery date in original no direct exposure to sunshine	
in	The raw material can be disposed of in an iendly manner. No toxic gases are released during icineration, as no PVC is used. The ground water is not ontaminated by toxic substances when dumped.	

The raw materials used in manufacture are physiologically harmless.

This product specification is the property of SENGEWALD Klinikprodukte GmbH and is to

be treated with the strictest confidence. Communication to third parties and duplication,

in whole or in part, are not permitted.